

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date  
12 May 2005 (12.05.2005)

PCT

(10) International Publication Number  
**WO 2005/042797 A1**

(51) International Patent Classification\*: C23C 14/56. (81) Designated States (unless otherwise indicated, for every kind of national protection available): AB, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number: PCT/SE2004/001603

(22) International Filing Date: 3 November 2004 (03.11.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 0302902-2 4 November 2003 (04.11.2003) SE

(71) Applicant (for all designated States except US): SANDVIK AB (publ) [SE/SB]; S-811 81 Sandviken (SE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): HOLMBERG, Håkan [SE/SB]; Tibastvägen 6, S-802 69 Gävle (SE).

(74) Agent: MELIN, Linda; Sandvik AB, Intellectual Property, S-811 81 Sandviken (SE).

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).


Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: A STAINLESS STEEL STRIP COATED WITH A METALLIC LAYER

BEST AVAILABLE COPV



WO 2005/042797 A1

(57) Abstract: The invention provides a coated high strength stainless steel strip (2) product with a dense and evenly distributed metallic layer (1, 3) on one side or both sides of said strip. Said layer consists of essentially pure gold, copper, nickel, cobalt, molybdenum, silver, tin or tungsten or alloys of at least 2 of these metals, the thickness of said layer is preferably maximally 15 µm, the tolerance of said layer is maximally +/- 30 % of the layer thickness, the Cr content of the steel strip substrate is at least 10 % and, and that the layer has such a good adhesion so that the coated steel strip can be uniaxially stretched to fracture by tensile testing without showing any tendency to peeling, flaking or the like. The metal-coated strip product is suitable for use in applications that are load carrying and must be able to transfer electrical currents to a contracting surface without an electrical conductivity drop at the interface between the surfaces.